

HumiSeal[®] 1A67 Urethane Conformal Coating

Technical Data Sheet

HumiSeal[®] 1A67 is a single component, polyester urethane conformal coating intended for the protection of general printed circuit assemblies. HumiSeal[®] 1A67 is a toluene-free coating with low gas permeability. HumiSeal[®] 1A67 demonstrates excellent flexibility and long term electrical properties and is RoHS Directive 2002/95/EC compliant.

Properties of HumiSeal[®] 1A67

Density, per ASTM D1475	0.92 g/cm ³
Solids Content, % by weight per Fed-Std-141, Meth. 4044	30 %
Viscosity, per Fed-Std-141, Meth. 4287	750 +/- 350 centipoise
VOC	644 grams/litre
Drying Time to Handle per Fed-Std-141, Meth. 4061	25 minutes
Recommended Coating Thickness	25 - 75 microns
Recommended Curing Conditions	20 hrs @ 80°C
Time Required to Reach Optimum Properties	7 days
Recommended Thinner	HumiSeal [®] Thinner 600
Recommended Stripper	HumiSeal [®] Stripper 1063
Glass Transition Temperature - DSC	55°C
Shelf Life at Room Temperature, DOM	12 months
Dielectric Withstand Voltage, per MIL-I-46058C	>1500 volts
Insulation Resistance, per MIL-I-46058C	6.93 x 10 ¹² ohms (6.93 TΩ)
Moisture Insulation Resistance, per MIL-I-46058C	6.9 x 10 ¹⁰ ohms (69 GΩ)

Application of HumiSeal[®] 1A67

Cleanliness of the substrate is of extreme importance for the successful application of a conformal coating. Surfaces must be free of moisture, dirt, wax, grease, and all other contaminants. Otherwise, ionic or organic residues on the substrate could be trapped under the coating and cause problems with adhesion or electrical properties. The highest long term reliability for a coated printed circuit assembly will be when the conformal coating is applied over a clean, dry substrate.

The application of conformal coatings over no clean flux is a common practice. The user should perform adequate testing to confirm compatibility between the conformal coating and their particular assembly materials and process conditions. Please contact HumiSeal for additional information.

Spraying

HumiSeal[®] 1A67 can be sprayed using conventional spraying equipment. Spraying should be done in an environment with adequate ventilation so that the vapour and mist are carried away from the operator. The addition of HumiSeal[®] Thinner 600 is necessary to ensure a uniform spray pattern resulting in pinhole-free film. The amount of thinner and spray pressure will depend on the specific type of spray equipment used and operator technique.

Brushing

HumiSeal[®] 1A67 may be brushed with a small addition of HumiSeal[®] Thinner 600. Uniformity of the film depends on component density and operator's technique.



HumiSeal®

HumiSeal® 1A67 Technical Data Sheet

Storage

HumiSeal® 1A67 should be stored away from excessive heat or cold, in tightly closed containers. HumiSeal® products may be stored at temperatures of 0 to 35°C. Prior to use, allow the product to equilibrate for 24 hours at a room temperature of 18 to 32°C.

Caution

Application of HumiSeal® Conformal Coatings should be carried out in accordance with local and National Health and Safety regulations.

The solvents in HumiSeal® Conformal Coatings are flammable. Material should not be used in presence of open flame or sparks. Use only in well-ventilated areas to avoid inhalation of vapours or spray. Avoid contact with skin and eyes.

Consult MSDS/SDS prior to use.

Contact HumiSeal®

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal Europe Support

Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrieres-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.